

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification: A61K 7/025, 7/027, 7/031, 7/032	AJ	(11) International Publication Number: WO 98/42298 (43) International Publication Date: 1 October 1998 (01.10.98)
(21) International Application Number: PCT/US98/04704 (22) International Filing Date: 12 March 1998 (12.03.98) (30) Priority Data: 08/824,510 26 March 1997 (26.03.97) US (71) Applicant: AVON PRODUCTS, INC. (US/US); 1251 Avenue of the Americas, New York, NY 10020-1196 (US). (72) Inventors: CURTIS, Ernest, S.; 423 Leisure Loop, Milford, PA 18337 (US). SHAH, Arvind, N.; 7 Mountainview Avenue, Suffern, NY 10901 (US). PAHLCK, Harold, E.; 36 Leonard Drive, Walldwick, NJ 07463 (US). (74) Agent: RUGGIERO, Charles, N., J.; Ohlandt, Greeley, Ruggiero & Potts, Suite 903, One Landmark Square, Stamford, CT 06901 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW). Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM). European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: WEAR RESISTANT COSMETICS (57) Abstract A wear-resistant cosmetic composition including a styrene-ethylene/propylene mixed block copolymer, preferably from about 0.1 weight percent to about 15 weight percent, in a cosmetically acceptable carrier. The cosmetic composition may also include an alkyl cycloalkylacrylate copolymer, preferably from about 0.1 weight percent to about 15 weight percent.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LG	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AY	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SE	Sweden
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BB	Barbados	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BE	Belgium	GR	Greece	ML	Mali	TR	Turkey
BF	Burkina Faso	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BG	Bulgaria	IE	Ireland	MR	Mauritania	UA	Ukraine
BJ	Benin	IL	Israel	MY	Malawi	UG	Uganda
BH	Bahrain	IS	Iceland	MX	Mexico	US	United States of America
BI	Burundi	IT	Italy	NE	Niger	UZ	Uzbekistan
BJ	Benin	JP	Japan	NL	Netherlands	VN	Viet Nam
BO	Bolivia	KE	Kenya	NO	Norway	YU	Yugoslavia
BR	Brazil	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
BS	Bahamas	KR	Democratic People's Republic of Korea	PL	Poland		
BT	Bhutan	KW	Republic of Korea	PT	Portugal		
BZ	Belize	KZ	Kazakhstan	RO	Romania		
CA	Canada	LC	Saint Lucia	RU	Russian Federation		
CC	Cocos (Keeling) Islands	LI	Liechtenstein	SD	Sudan		
CD	Congo	LU	Luxembourg	SE	Sweden		
CE	Cote d'Ivoire	LV	Latvia	SG	Singapore		
CF	Congo	LB	Lebanon				
CG	Congo						
CH	Switzerland						
CI	Cote d'Ivoire						
CJ	Cameroon						
CK	China						
CL	Cuba						
CM	Cameroon						
CN	China						
CO	Congo						
CR	Costa Rica						
CS	Czech Republic						
CU	Cuba						
CV	Cape Verde						
CY	Cyprus						
CZ	Czech Republic						
DE	Germany						
DF	Dominican Republic						
DG	Dominican Republic						
DH	Dominican Republic						
DI	Dominican Republic						
DJ	Dominican Republic						
DK	Denmark						
DL	Dominican Republic						
DM	Dominican Republic						
DN	Dominican Republic						
DO	Dominican Republic						
DP	Dominican Republic						
DQ	Dominican Republic						
DR	Dominican Republic						
DS	Dominican Republic						
DT	Dominican Republic						
DU	Dominican Republic						
DV	Dominican Republic						
DW	Dominican Republic						
DX	Dominican Republic						
DY	Dominican Republic						
DZ	Dominican Republic						

WEAR RESISTANT COSMETICS

The present invention relates generally to wear resistant cosmetic compositions. More particularly, this invention relates to a cosmetic composition
5 containing a styrene-ethylene/propylene mixed block copolymer that demonstrates enhanced wear in combination with a smooth, non-tacky feel.

BACKGROUND OF THE INVENTION

10 Various organic waxes and film formers are known in the art for their ability to impart uniform films and protective barriers to the skin and lips. Most of these films are slow to dry on application. Because these films remain wet for extended periods
15 of time, they adhere poorly and tend to transfer off the surface to which they are applied. This results in poor overall cosmetic wear, and requires that the user reapply the cosmetic frequently.

Those film formers that provide somewhat more
20 rapid drying times have additional limitations. The primary limitation of these film formers is an unpleasant tacky feel on application to the skin, lips or lashes that is disliked by consumers. Also, these products tend to drag against the skin when
25 applied, and leave the skin feeling dry and sticky.

Accordingly, there is a need for a wear-resistant cosmetic that forms a protective film on the skin that is also quick to dry and easy to apply, but does not have an unpleasant, undesirable tacky
30 feel on the skin.

SUMMARY OF THE INVENTION

Against the foregoing background, it is a primary object of the present invention to provide a
35 cosmetic composition having enhanced wear resistance.

It is another object of the present invention to provide a cosmetic composition that produces a quick drying protective film on the skin.

It is yet another object of the present invention to provide a wear resistant cosmetic composition that is not tacky and neither drags against the skin upon application nor dries the skin.

To the accomplishment of the foregoing objects and advantages, the present invention, in brief summary, comprises a wear-resistant cosmetic composition including a styrene-ethylene/propylene mixed block copolymer, preferably at from about 0.01 weight percent to about 85 weight percent, in a cosmetically acceptable carrier. The cosmetic composition may also include an alkyl cycloalkylacrylate copolymer, preferably at from about 0.01 weight percent to about 85 weight percent.


DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present invention provides a wear-resistant cosmetic such as, for example, a lipstick, foundation, eye shadow, blush or mascara. It has surprisingly been found that a styrene-ethylene/propylene mixed block copolymer provides superior wear resistance to such cosmetic compositions or formulas, both alone and preferably in combination with an alkyl cycloalkylacrylate copolymer. Moreover, it has surprisingly been found that cosmetic formulas containing the styrene-ethylene/propylene mixed block copolymer are non-tacky and have a pleasant feel when applied to the skin. These compositions are easy to apply, have improved skin and lip adherence (transfer resistance), and provide enhanced wear and longevity.

Most preferably, the wear-resistant cosmetic composition according to the present invention includes a styrene-ethylene/propylene mixed block copolymer in a cosmetically acceptable carrier. This
 5 cosmetic composition may also include an alkyl cycloalkylacrylate copolymer as a primary ingredient or in combination with the mixed-block copolymer.


The preferred styrene-ethylene/propylene mixed block copolymer of the present invention is a block
 10 copolymer made up of styrene, ethylene and propylene type monomers having the following general structure:

Styrene




15


Ethylene



Propylene



20 where R_1 to R_6 are independently hydrophobic alkyl chains. One possible structure of the copolymer, with the repeating monomer subset shown in brackets, is:



wherein $n \geq 1$ and the R groups may be the same or different, and are independently hydrophobic alkyl chains.


The most preferred styrene-ethylene/propylene mixed block copolymer for use in the present invention is available from Brooks Industries as Gel Base (Code 05895). Gel Base (Code 05895) is a styrene-ethylene/propylene mixed block copolymer in combination with isododecane, that is provided as a cloudy white gel. The specific structure of the Gel Base (Code 05895) styrene-ethylene/propylene mixed block copolymer is proprietary to Brooks Industries.

This mixed block copolymer is not water soluble, but is soluble in certain oils and hydrocarbon solvents such as isoparaffin and isododecane. This allows the mixed block copolymer to be delivered in a volatile solvent base to the skin. Once delivered, the volatile solvent evaporates, at least partially, leaving the water insoluble mixed block copolymer film on the skin. This film resists transfer and wear. The mixed block copolymer is most preferably used in combination with a silicone-containing base (containing, for example, dimethicone/cyclomethicone) or an organic volatile in an aqueous base, for superior feel and wear.


In a preferred embodiment, the styrene-ethylene/propylene mixed block copolymer is from about 0.01 percent by weight to about 85 percent by weight (weight percent) of the total weight of the composition. In the most preferred embodiment, the styrene-ethylene/propylene mixed block copolymer is from about 0.1 to about 15 percent by weight of the composition. It should be understood that one or more styrene-ethylene/propylene mixed block copolymers may be used in the present compositions.

When the composition includes the alkyl-cycloalkylacrylate copolymer, the preferred alkyl-cycloalkylacrylate copolymer is a copolymer or copolymers having the following formulas and the isomers thereof:

Structure A



Structure B



where R_1 to R_4 are independently hydrophobic alkyl chains. The alkyl cycloalkylacrylate copolymers are soluble in hydrocarbons, such as isododecane, but not in water, thus enhancing the film-forming effect of the copolymer in a volatile solvent base.

When included, the alkyl cycloalkylacrylate copolymer or copolymers can be from about 0.01 percent by weight to about 85 percent by weight. Preferably, this copolymer is about 0.1 percent by weight to about 15 percent by weight of the composition.

The composition may also include other ingredients, such as a volatile solvent, wax, powder, non-volatile oil, and emulsifier.

The volatile solvent of the present invention acts as a carrier for the other components of the cosmetic, rapidly and evenly dispersing them on the skin, and then evaporating. The preferred volatile solvent includes C_6 to C_{20} hydrocarbon fractions, more preferably an isoparaffin and most preferably the specific C_{12} fraction isododecane. Alternatively, cyclomethicone, up to a preferred limit of about 30 weight percent, is also favored.

The volatile solvent may be present in an amount from about 0.01 percent by weight to about 85 percent by weight. However, in certain compositions, less volatile solvent than the maximum 85 percent by weight is desired. For example, a foundation preferably contains no more than about 50 percent by weight of volatile solvent. One or more volatile solvents may be present in the above total amount.

The preferred wax or waxes can be of vegetable, synthetic or hydrocarbon origin. The wax preferably should have a melting point in the range between about 35°C to 120°C. The wax is present in an amount from about 0.01 percent by weight to about 50 percent by weight of the composition. A greater amount of wax is preferred in an anhydrous blush or lipstick than in a mascara. Therefore, the amount of wax in an anhydrous blush or lipstick is preferably about 0.01 percent by weight to about 50 percent by weight, whereas in a mascara, the amount of wax is preferably about 0.01 to about 25 percent by weight of the composition.

The dry powder, as discussed above, gives color and sheen to the cosmetics of the present composition. The preferred dry powder includes an organic or an inorganic powder or a combination thereof. The dry powder preferably is a certified organic lake, a stain or an inorganic pigment having a particle size between about 0.02 and about 85 microns in diameter. The dry powder or powders component is preferably present in an amount from about 0.1 percent by weight to about 65 percent by weight of the composition, with the higher figure most suitable for such products as lipsticks or foundations. A blush or mascara preferably contains no more than about 20 to 25 weight percent of powder.

It is also preferred, depending on the final product being formulated, to include a nonvolatile oil, emulsifier, water or a combination thereof to the finished cosmetic composition. The copolymers of
5 the present invention are suitable for use in both water-based and anhydrous systems.

A preferred cosmetic composition according to the present invention comprises from about 0.01 weight percent to about 85 weight percent of a block
10 copolymer of styrene, ethylene and propylene type monomers. In a more preferred embodiment, the composition also includes from about 0.01 weight percent to about 85 weight percent of alkyl cycloalkylacrylate copolymer. Another preferred
15 cosmetic composition according to the present invention comprises:

- 1) from about 0.01 weight percent to about 85 weight percent of a block copolymer of styrene, ethylene and propylene type monomers;
- 20 2) from about 0.01 weight percent to about 85 weight percent of alkyl cycloalkylacrylate copolymer;
- 3) from about 0.01 weight percent to about 85 weight percent volatile solvent;
- 4) from about 0.01 weight percent to about 50
25 weight percent wax;
- 5) from about 0.1 weight percent to about 65 weight percent dry powder; and
- 6) from about 0.01 weight percent to about 80 weight percent non-volatile oil, emulsifier and/or
30 water.

As discussed above, one or more of each ingredient may be used, but with the total amount of that ingredient set forth above.

Within the preferred ranges set forth above, the
35 following Examples 1 through 3 set forth preferred

subset compositions for foundations, blushes or lipsticks, and mascaras, respectively.

Example 1

5

FOUNDATION

		<u>Wt. %</u>	
		<u>From about</u>	<u>To about</u>
	Styrene-ethylene/propylene mixed block copolymer	0.01	15
10	Alkyl cyclomethacrylate copolymer	0.01	15
	Volatile Solvent	0.01	50
	Wax	0.01	30
	Powder	0.1	65
15	Nonvolatile oil, emulsifier and water	0.01	55

Example 2

20

ANHYDROUS BLUSH/LIPSTICK

		<u>Wt. %</u>	
		<u>From about</u>	<u>To about</u>
	Styrene-ethylene/propylene mixed block copolymer	0.01	10
25	Alkyl cyclomethacrylate copolymer	0.01	20
	Volatile Solvent	0.01	60
	Wax	0.01	50
	Powder	0.1	25
30	Nonvolatile oil and emulsifier	0.01	55

Example 3

MASCARA

35

		<u>Wt. %</u>	
		<u>From about</u>	<u>To about</u>
	Styrene-ethylene/propylene mixed block copolymer	0.01	30
	Alkyl cyclomethacrylate copolymer	0.01	50
40	Volatile Solvent	0.01	70
	Wax	0.01	25

Powder	0.1	20
Nonvolatile oil, emulsifier and water	0.01	50

5 The following are illustrative preferred
embodiments.

Example 4 - Pigmented Foundation

10	Isododecane	25.00
	Silica-fumed	0.50
	Isooctahexacontane	1.00
	Bentone gel	3.00
	Isododecane/mixed block	
15	copolymer	6.00
	Cycloalkylmethacrylate	
	copolymer/isododecane	2.00
	Laurylmethicone copolyol	2.00
	Polyglycerol diisostearate	0.75
20	Glyceryl tribehenate	0.75
	Glyceryl rosinat	4.00
	Cosmetic powder	8.75
	Cosmetic pigment	12.693
	Demineralized water	27.785
25	Disodium EDTA	0.20
	Sodium hexametaphosphate	0.15
	Sodium chloride	0.50
	Butylene glycol	4.00
	Methylparaben	0.40
30	Xanthan gum	0.01
	Imidazolidinyl urea	0.50

Example 5 - Waterproof Mascara

	Odorless Mineral Spirits	32.35
35	Isododecane/Mixed Block	
	Copolymer	15.00
	Cycloalkylmethacrylate	
	copolymer/isododecane	4.00
	Pentaerythritol rosinat	2.50
40	Iron oxide	5.00
	Cosmetic wax	9.30
	Cosmetic powder	13.00
	Hydroxylated lanolin	1.30
	Glyceryl Pyroglutamate	
45	Monooleate	0.50
	Polybutene	0.10
	Butylated hydroxytoluene	0.02
	Propylparaben	0.26
	Demineralized water	14.88

	Polyvinylpyrrolidone	0.10
	Tetrasodium EDTA	0.20
	Acetylated POE lanolin	
	alcohol	0.20
5	Propylene glycol	1.00
	Methylparaben	0.30
	2-phenoxyethanol	0.50

10 Example 6 - Blush

	Tridecyl trimellitate	14.68
	Isododecane/mixed block	
	copolymer	4.95
15	Isododecane	7.35
	Cyclomethicone	4.50
	Cycloalkylmethacrylate	
	copolymer/isododecane	20.00
	Pentaerythritol rosinat	1.20
20	Isopropyl lanolate	5.00
	Cosmetic wax	22.00
	BHT	0.02
	Ethylhexyl palmitate	5.00
	Jojoba oil	0.50
25	Ethylhexyl methoxycinnamate	1.00
	Tocopherol acetate	0.05
	Organic pigment lake	0.55
	Iron oxide	1.35
	Titanium dioxide	3.85
30	Mica	8.00

Example 7 -- Lip Color

35	Cosmetic wax	14.60
	Diisostearyl fumarate	9.80
	Stearyl dimethicone	3.90
	Ethylhexyl methoxycinnamate	3.20
	Benzophenone 3	1.50
40	Iron oxide pigment	9.60
	Cosmetic powder	2.84
	Cyclomethicone	45.05
	Isododecane	6.00
	Isododecane/mixed block	
45	copolymer	2.00
	Squalane	1.50
	Cycloalkylmethacrylate	
	copolymer/isododecane	0.01

50


The invention having been thus described with particular reference to the preferred forms thereof,

it will be obvious that various changes and modifications may be made therein without departing from the spirit and scope of the invention as defined in the appended claims.

What we claim is:

1. A wear-resistant cosmetic composition comprising a styrene-ethylene/propylene mixed block copolymer in a cosmetically acceptable carrier.

2. The cosmetic composition of claim 1, wherein said styrene-ethylene/propylene mixed block copolymer is of a structure as follows:



wherein $n \geq 1$ and R represents independently hydrophobic alkyl groups of identical or different types.


3. The cosmetic composition of claim 1, wherein said styrene-ethylene/propylene mixed block copolymer is present from about 0.01 percent by weight to about 85 percent by weight of a total composition weight.

4. The cosmetic composition of claim 1, wherein said styrene-ethylene/propylene mixed block copolymer is present from about 0.1 weight percent to about 15 percent by weight of a total composition weight.


5. The cosmetic composition of claim 1, further comprising an alkyl cycloalkylacrylate copolymer.

6. The cosmetic composition of claim 5, wherein said alkyl cycloalkylacrylate copolymer is of a structure selected from the group consisting of Structure A, Structure B, an isomer of Structure A, an isomer of Structure B, and a combination thereof:

Structure A



Structure B



where R1 to R4 are independently hydrophobic alkyl chains.

7. The cosmetic composition of claim 5,
5 wherein said alkyl cycloalkylacrylate copolymer is present at from about 0.01 weight percent to about 85 weight percent.

8. The cosmetic composition of claim 5,
10 wherein said alkyl cycloalkylacrylate copolymer is present at from about 0.1 weight percent to about 15 weight percent.

9. The cosmetic composition of claim 1,
15 wherein said carrier comprises a volatile solvent.

10. The cosmetic composition of claim 9,
wherein said volatile solvent is present at from about 0.01 weight percent to about 85 weight percent.
20

11. The cosmetic composition of claim 10,
wherein said volatile solvent includes a volatile hydrocarbon.

25 12. The cosmetic composition of claim 10,
wherein said volatile solvent is silicon-based.

13. The cosmetic composition of claim 1,
wherein said carrier includes a volatile hydrocarbon.
30

14. The cosmetic composition of claim 1,
wherein said carrier includes silicone.

15. The cosmetic composition of claim 1,
further comprising from about 0.01 weight percent to
about 50 weight percent wax.

5 16. The cosmetic composition of claim 1,
further comprising from about 0.1 weight percent to
about 65 weight percent dry powder.

17. The cosmetic composition of claim 1,
10 wherein said carrier comprises water.

18. The cosmetic composition of claim 1,
further comprising a non-volatile oil.

15 19. The cosmetic composition of claim 1,
further comprising an emulsifier.

20. A wear-resistant cosmetic composition
comprising an alkyl cycloalkylacrylate copolymer.
20

21. A wear-resistant cosmetic composition
comprising:

from about 0.01 to about 30 percent by weight
styrene-ethylene/propylene mixed block copolymer;

25 from about 0.01 to about 50 percent by weight
alkyl cyclomethacrylate copolymer;

from about 0.01 to about 70 percent by weight
volatile solvent;

from about 0.01 to 50 percent by weight wax; and
30 from about 0.1 to 65 percent powders.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US98/04704

A. CLASSIFICATION OF SUBJECT MATTER

IPC(8) : A61K 7/023, 7/027, 7/031, 7/032

US CL : 424/64, 70.7, 401

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/64, 70.7, 401

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

NONE

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,558,872 A (JONES et al.) 24 September 1996, column 2, line 26 and claim 1.	1-4
Y		9-19
Y	US 5,219,560 A (SUZUKI et al.) 15 June 1993, abstract, columns 11-14, and examples.	9-19

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* "A"	document defining the general state of the art which is not considered to be of particular relevance	* "Y"	document published after the international filing date or priority date and not in conflict with the application but aimed to understand the principle or theory underlying the invention
* "R"	earlier documents published on or after the international filing date	* "X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to operate on inventive step when the document is taken alone
* "L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another document or other special reason (to be specified)	* "Y"	document of particular relevance; the claimed invention cannot be considered to have an inventive step when the document is combined with one or more other such documents, each contribution being obvious to a person skilled in the art
* "O"	document referring to an oral disclosure, use, exhibition or other means	* "G"	document in respect of the same patent family
* "P"	document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

29 MAY 1998

Date of mailing of the international search report

22 JUN 1998

Writer and printing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-4363

Authorized officer

JYOTHSNA VENKAT

Telephone No. (703) 306-3493

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.